



## TECHNICAL DATA SHEET

### **Everchem DMP-30**

#### **Description**

Everchem DMP-30 is an amine-based, delayed-action trimerization catalyst for rigid polyisocyanurate foams and can be used in CASE applications.

#### **Applications**

Everchem DMP-30 is widely used for the production of rigid polyisocyanurate boardstock. It is typically used in combination with other standard amine catalysts

<b>Typical Properties</b>	
Flash Point, °C (PMCC)	150
Viscosity @25°C mPa.s	201
Specific Gravity @25°C (g/cm <sup>3</sup> )	0.97
Water Solubility	Soluble
Calculated OH Number (mgKOH/g)	213
Appearance	Light yellow liquid

#### **Shelf Life:**

12 Months

#### **Standard Packaging:**

- 200KG Steel Drum
- IBC Drum is recommended.

#### **Storage Information**

Recommends that our catalysts be stored in a dry and cool area under appropriate ventilation conditions.

The optimum storage temperature is between 10 °C and 30 °C. Lower and higher storage temperatures are not preferable and should be avoided.

*The information contained in this sheet is correct and accurate and is based on our technical and scientific knowledge and on literature at the date of going to press. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing stated here may be taken or construed as implying of any existing patents. Nor is any warranty, whether explicit or implicit, given with regard to results to be obtained through the use of the aforesaid information.*

#### **Everchem, LLC**

1400 N. Providence Road, Ste 302  
Media, PA 19063

[www.everchem.com](http://www.everchem.com)

TEL: (484) 234-5030

FAX: (484) 234-5037